

Datasheet – Rototuff™ RT3930UV

Rototuff™ RT3930UV is a Hexene Co-polymer Linear Low Density Polyethylene (LLDPE) which provides a good balance of rigidity and toughness. Rototuff™ RT3930UV has been formulated to provide a UV20 level of protection for Australian conditions with previous wide acceptance by moulders in the Australian market.

The base resin for Rototuff™ RT3930UV is AS/NZS4766:2020 certified and complies with the Food and Drug Administration (FDA) Specifications according to U.S.FDA 21 Code of Federal Regulations part 177.1520 (c) 3.2a use conditions B through H for articles coming into contact with food.

Properties ¹	Test Method	Value	Units
MFI (190 degC; 2.16kg)	ASTM D1238	3.0	g/10min
Density	ASTM D1505	0.939	g/cm ³
Tensile @ Yield ²	ASTM D638	17	MPa
Elongation @ Break ²	ASTM D638	700	%
Flexural Modulus ³	ASTM D790	820	MPa
ESCR ⁴	ASTM D1693	1000	Hours
UV Resistance ⁵	AS/NZS4766	UV20	-
Melting Temperature	ASTM D3418	128	°C

¹ Base Resin Properties

² Crosshead Speed @ 50mm/min

³ Crosshead Speed @ 12.7mm/min

⁴ F50; 100% Igepal; Condition A

⁵ Greater than 50% retained tensile elongation after 20,000 hrs accelerated UV exposure.

Disclaimer: The information set out above is based on data provided by our suppliers and the values shown reflect those of the base resin only. The addition of pigments has a marginal effect on density dependent on colour and addition rates used. Data has been used in good faith and no responsibility can be accepted by us for its accuracy or for any claims or proceedings, (including direct or indirect consequences arising from any claims or proceedings) or any direct or indirect loss or damage arising from the accuracy, use of or reliance upon this information. To the extent permitted by law, all warranties, representations, conditions whether expressed or implied by law, trade custom or otherwise in respect of this information are also expressly excluded.